

**Article number:** EDF – 61671

## Technical Data Sheet

---

### PRODUCT DESCRIPTION:

High-pressure decorative laminates with enhanced fire resistance, designed for outdoor use in moderate and heavy conditions, exposed to direct sunlight, rain and frost. They feature an attractive and aesthetic appearance, high tensile strength, impact, thermal shock, weather and corrosion.

Available in dimensions:

- thickness: 6, 8, 10 [mm],
- size: 2800 x 2040 [mm], 3050 x 1300 [mm], 4200 x 1300 [mm], 5600 x 2040 [mm].
- Other dimensions available on request.

---

### APPLICATION:

- Building industry - elevations
- Built-up of a free spaces, partitions, cubicles, wall cladding
- Balconies

---

### STORAGE:

KronoArt Boards should be stored in a dry and roofed placing, at temperatures of 15-25°C, relative humidity of 50%, min. 1,5m distance to source of heat. Keeping in humid conditions with water on the surface might lead to bending KronoArt boards what should be avoided.

It is recommended to store in the original Kronospan packaging, on pallets. In the case of foiled boards, the foil should be removed immediately before assembly.

**Article number:** EDF – 61671

## Technical Data Sheet

### PROPERTIES:

Parameter	Unit	Standard	Requirements
Thickness	mm	438-2.5	6,0 ≤ t < 8,0 ± 0,40 8,0 ≤ t < 12,0 ± 0,50 12,0 ≤ t < 13,0 ± 0,60
Length	mm	438-2.6	+10/ - 0
Width	mm	438-2.6	+10/ - 0
Flatness	mm/m	438-2.9	2,0 ≤ t < 6,0 ≤ 8,0 6,0 ≤ t < 10,0 ≤ 5,0 t ≥ 10,0 ≤ 3,0
Straightness of edges	mm/m	438-2.7	≤ 1,5
Squarerness	mm/m	438-2.8	≤ 1,5
Resistance to aging in artificial conditions, including UV	Grey scale rating	438-2.29	≥ 3 (3000h)
	Appearance, grade		≥ 4 (3000h)
Resistance to impact with large diameter ball	Drop height, [mm]	438-2.21	2,0 ≤ t < 6,0 ≥ 1400 t ≥ 6,0 ≥ 1800
Resistance to wet conditions	Mass gain [%]	438-2.15	2,0 ≤ t < 5,0 ≤ 10 t ≥ 5,0 ≤ 8
	Appearance, surface rating		≥ 4
	Appearance, edge rating		≥ 3
Dimensional stability at elevated temperature	Cumulative dimensional change, [%]	438-2.17	2,0 ≤ t < 5,0 0,40/0,80 t ≥ 5,0 0,30/0,60
Flexural modulus	[MPa]	EN ISO 178	≥ 9000
Flexural strength	[MPa]	EN ISO 178	≥ 80
Tensile strength	[MPa]	EN ISO 527-2	≥ 60
Density	[g/cm <sup>3</sup> ]	EN ISO 1183-1	≥ 1,35
Fire class	Classification	EN 13501-1	B-s1, d0

t – nominal thickness

**Additional information:**

The contents of this document are for informational purposes only. Possible mistakes are possible. Customers and third parties are obliged to obtain information about Kronospan products and their usage. We strongly recommend the recipient or user of our products to obtain expert advice regarding compliance with local planning, application requirements, standards, norms etc. Kronospan does not accept any warranties for claims relating to this document.

Prepared: M. Szablowska  
Date: 26.01.2018

Checked: T. Tabor  
Date: 26.01.2018

Approved: R. Doehring  
Date: 26.01.2018